



19. 耐隆粒



❖ 特性(Characteristics)

耐隆 6 粒(切片Nylon 6 Chip)

光澤(Luster)：亮光絲(BR)、半光絲(SD)、鈍光絲(消光FD)

❖ 用途：

1	1N：半光低粘度(SD)	長纖紡絲(Filament Grade)
2	1F：鈍光低粘度(FD)	長纖紡絲(Filament Grade)
3	2N：亮光低粘度(BR)	長纖紡絲(Filament Grade)
4	3N：半光中粘度(SD)	長纖紡絲(Filament Grade)
5	4N：亮光中粘度(BR)	長纖紡絲(Filament Grade)
6	6N：亮光高粘度(BR)	工業用絲(Industrial Filament) 工程塑膠(Engineering Plastic) 短纖(Staple Fiber)
7	6Q：亮光高粘度(BR)	工業單絲(Mono Filament) 短纖(Staple Fiber)





19. 耐隆粒—續

❖ 規格及物性(Specifications & Physical Properties)

Item	Luster	R.V.	Extractable Content (%)	M.P (°C)	ASH(%)	Water Content(%)
1N	SD	2.455~2.485	≤0.32	220±5	0.29±0.2	0.045~0.075
1F	FD	2.455~2.485	≤0.32	220±5	1.55±0.05	0.045~0.075
2N	BR	2.450~2.480	≤0.32	220±5	0	0.045~0.075
3N	SD	2.895~2.925	≤0.32	221±5	0.29±0.2	0.045~0.075
4N	BR	3.050~3.080	≤0.32	221±5	0	0.045~0.075
6N	BR	3.440~3.480	≤0.34	223±5	0	0.045~0.075
6Q	BR	3.240~3.280	≤0.34	222±5	0	0.045~0.075

